

Colour Copy Coated Gloss (ECF)

Technical Information

	√ = amendment	+ = addition	X = deletion		
Substance g/m ²	135	170	200	250	
Caliper μm (approx)	107	140	160	215	
Opacity (ISO) %	96	98	-	-	
Brightness (ISO) % D65	100	100	100	100	
Whiteness CIE D65	134	134	134	134	
Gloss (Gardner) 75°	77	77	77	77	
Rigidity (Taber) 15° MD	4.1	11	18	37	
Stiffness Units CD	2.8	5.8	12	22	
Surface pH	9.3	9.3	9.3	9.3	

Environmental Information

FIBRE SOURCE

Virgin wood fibre from Canada, USA, Europe, Morocco, and Brazil.

BLEACHING


Pulp is bleached using an Elemental Chlorine Free (ECF) process.

DISPOSAL

This material can be disposed of by recycling and incineration for energy.

Technical Capability

Guaranteed for Digital Colour Laser Systems
Meets ISO9706 requirements for the Permanence of Paper

© **Information contained in this specification sheet is the Copyright of**  Robert Horn Group
Purelypaper Ltd provides all information in good faith,
but may not be held liable for loss or damage arising from action based on this leaflet.