

## Colour Copy Coated Silk (ECF)

### Technical Information

√ = amendment      + = addition      X = deletion

Substance g/m <sup>2</sup>	135	170	200	250	
Caliper μm (approx)	110	156	188	240	
Opacity (ISO) %	96.5	98	-	-	
Brightness (ISO) % D65	102	102	102	102	
Whiteness CIE D65	134	134	134	134	
Gloss (Gardner) 75°	55	55	55	55	
Smoothness (Bendsten) TS ml/min WS	10 10	10 10	10 10	10 10	
Rigidity (Taber) 15° MD Stiffness Units CD	4.7 2.9	16.0 7.2	23.5 16.5	49 32	
Surface pH	9.3	9.3	9.3	9.3	

### Environmental Information

#### FIBRE SOURCE

Virgin wood fibre from Canada, Europe, Morocco, and Brazil.

#### BLEACHING


Pulp is bleached using an Elemental Chlorine Free (ECF) process.

#### DISPOSAL

This material can be disposed of by recycling.

### Technical Capability

Guaranteed for Digital Colour Laser Systems  
Meets ISO9706 requirements for the Permanence of Paper

© Information contained in this specification sheet is the Copyright of  Robert Horn Group  
Purelypaper Ltd provides all information in good faith,  
but may not be held liable for loss or damage arising from action based on this leaflet.