

HP Copy (ECF)

Technical Information

Substance g/m ²	107
Caliper µm (approx)	80
Opacity (ISO) %	92
Brightness (ISO) %	94
Whiteness CIE D65	142
Smoothness (Bendtsen) TS	200
ml/min WS	200
Rigidity (Taber) 15° MD	3.0
Stiffness Units CD	1.3
Surface pH	7.8

Environmental Information

FIBRE SOURCE

Virgin wood fibre from France.

BLEACHING

Pulp is bleached using an Elemental Chlorine Free (ECF) Process.

DISPOSAL

This material can be disposed of by recycling, incineration for energy.

ACCREDITATION

- Produced at a mill that is certified with the ISO14001 environmental management standard.
- Meets ISO9706 requirement for permanence of paper.

Technical Capability

Hi Speed Copiers & Printers	-	Guaranteed.
Inkjet Compatible	-	Yes.
Laser Compatible	-	Mono only.