

## HP PRINTING PAPER

Substance g/m <sup>2</sup>	80	90
Caliper µm (approx)	107	112
Opacity (ISO) %	92	94
Brightness (ISO) D65	109	109
Whiteness CIE D65	161	161
Smoothness (Bendtsen) ml/min TS	220	220
Smoothness (Bendtsen) ml/min WS	220	220
Rigidity (Taber Stiffness Units) 15° MD	2.8	2.9
Rigidity (Taber Stiffness Units) 15° CD	0.8	1.1
Surface pH	>7	>7

### Technical Capability

Copier Guaranteed	Yes, mono only
Laser Guaranteed	Yes, mono only
Inkjet Guaranteed	Yes, mono and colour
Plain Paper Fax	Yes
Permanence of Paper	Yes, meets ISO9706 requirements for Permanence of Paper

### Environmental Information

Fibre Source	Virgin wood fibre from France
Bleaching	Pulp is bleached using an Elemental Chlorine Free (ECF) process
Disposal	This material can be disposed of by recycling, incineration for energy recovery and composting
Accreditation	Produced at a mill that is certified with the ISO14001 environmental management standard PEFC Certified