

NAVIGATOR EXPRESSION

Substance g/m ²	90
Caliper µm (approx)	114
Opacity (ISO) %	96
Brightness (ISO) D65	112
Whiteness CIE D65	169
Smoothness (Bendtsen) ml/min TS	100
Smoothness (Bendtsen) ml/min WS	100
Rigidity (Taber Stiffness Units) 15° MD	4.1
Rigidity (Taber Stiffness Units) 15° CD	2
Surface pH	8.5

Technical Capability

Copier Guaranteed	Yes, mono only
Laser Guaranteed	Yes, mono only
Inkjet Guaranteed	Yes, mono and colour
Permanence of Paper	Yes, meets ISO9706 requirements for permanence of paper.

Environmental Information

Fibre Source	Virgin wood fibre from Portugal, Spain, South America and Sweden
Bleaching	Pulp is bleached using an Elemental Chlorine Free (ECF) process.
Disposal	This material can be disposed of by recycling
Accreditation	Produced at a mill that is certified to the ISO14001 environmental management standard. FSC Mix. Paper from responsible sources