

IBM ALL DAY

Substance g/m ²	80
Caliper μm (approx)	106
Opacity (ISO) %	90
Brightness (ISO) D65	107
Whiteness CIE D65	146
Smoothness (Bendtsen) ml/min TS	200
Smoothness (Bendtsen) ml/min WS	200
Rigidity (Taber Stiffness Units) 15° MD	2.4
Rigidity (Taber Stiffness Units) 15° CD	1.15
Surface pH	>7

Technical Capability

Laser Guaranteed	Yes, mono only
Inkjet Guaranteed	Yes, mono only
Permanence of Paper	Yes, meets ISO9706 requirements for Permanence of Paper

Environmental Information

Fibre Source	Virgin wood fibre from USA, Chile, Spain, Portugal, Canada and Sweden
Bleaching	Pulp is bleached using an Elemental Chlorine Free (ECF) process
Disposal	This material can be disposed of by recycling, incineration for energy recovery or composting
Accreditation	Produced at a mill that is certified to the ISO14001 environmental management standard PEFC Certified