

MOTIF ALL IN ONE

Substance g/m ²	80	90	100
Caliper µm (approx)	105	116	127
Opacity (ISO) %	92	94	95
Brightness (ISO) D65	110	115	115
Whiteness CIE D65	160	168	168
Smoothness (Bendtsen) ml/min TS	160	160	160
Smoothness (Bendtsen) ml/min WS	160	160	160
Rigidity (Taber Stiffness Units) 15° MD	2.1	3.1	4.3
Rigidity (Taber Stiffness Units) 15° CD	0.9	1.4	2.4
Surface pH	>7.0	>7.0	>7.0

Technical Capability

Copier Guaranteed	Mono
Laser Guaranteed	Mono, suitable for colour
Inkjet Guaranteed	Mono, suitable for colour
Permanence of Paper	Yes, meets ISO9706 requirements for Permanence of Paper

Environmental Information

Fibre Source	Virgin wood fibre from Sweden and Germany
Bleaching	Pulp is bleached using an Elemental Chlorine Free (ECF) process
Disposal	This material can be disposed of by recycling, incineration for energy recovery, composting and biodegradation
Accreditation	Produced at a mill that is certified to the ISO14001 environmental management standard Produced at a mill that is certified to the EMAS environmental management standard This product has the Nordic Swan accreditation FSC MIXed Sources product group from well managed forests and other controlled sources