

MOTIF COPY

Substance g/m ²	80
Caliper µm (approx)	105
Opacity (ISO) %	92
Brightness (ISO) D65	106
Whiteness CIE D65	149
Smoothness (Bendtsen) ml/min TS	220
Smoothness (Bendtsen) ml/min WS	220
Rigidity (Taber Stiffness Units) 15° MD	2.3
Rigidity (Taber Stiffness Units) 15° CD	1.4
Surface pH	7.7

Technical Capability

Copier Guaranteed	Mono
Laser Guaranteed	Mono
Inkjet Guaranteed	Mono
Permanence of Paper	Yes, meets ISO9706 requirements for Permanence of Paper

Environmental Information

Fibre Source	Virgin wood fibre mainly from Finland, Russia and Estonia
Bleaching	Pulp is bleached using an Elemental Chlorine Free (ECF) process
Disposal	This material can be disposed of by recycling, incineration for energy recovery, composting and biodegradation
Accreditation	Produced at a mill that is certified with the ISO14001 environmental management standard Produced at an EMAS registered mill (No. FI-000008) This product has the Nordic Swan accreditation PEFC Certified