

MOTIF PREMIUM

Substance g/m ²	80	90	100	120	160
Caliper µm (approx)	113	122	132	158	205
Opacity (ISO) %	93	95	96	98	99
Brightness (ISO) D65	116	116	116	116	116
Whiteness CIE D65	168	168	168	168	168
Smoothness (Bendtsen) ml/min TS	220	220	220	220	220
Smoothness (Bendtsen) ml/min WS	220	220	220	220	220
Rigidity (Taber Stiffness Units) 15° MD	2.9	3.3	4	5.3	18
Rigidity (Taber Stiffness Units) 15° CD	1.7	1.8	2.3	3.3	7
Surface pH	7.5	7.5	7.5	7.5	7.5

Technical Capability

Copier Guaranteed	Yes, mono
Laser Guaranteed	Yes, mono and colour
Inkjet Guaranteed	Yes, mono and colour
Permanence of Paper	Yes, meets ISO9706 requirements for Permanence of Paper

Environmental Information

Fibre Source	Virgin wood fibre Sweden and Brazil
Bleaching	Pulp is bleached using an Elemental Chlorine Free (ECF) process
Disposal	This material can be disposed of by recycling, incineration for energy recovery, composting and biodegradation
Accreditation	Produced at a mill that is certified to the ISO14001 environmental management standard Produced at an EMAS registered mill (No S-000090) FSC Mixed Sources product group from well managed forests and other controlled sources