

YOYO FRESH WHITE

Substance g/m ²	80
Caliper μm (approx)	103
Opacity (ISO) %	92
Brightness (ISO) D65	106
Whiteness CIE D65	146
Smoothness (Bendtsen) ml/min TS	250
Smoothness (Bendtsen) ml/min WS	320
Rigidity (Taber Stiffness Units) 15° MD	2.6
Rigidity (Taber Stiffness Units) 15° CD	1.4
Surface pH	7.8

Technical Capability

Copier Guaranteed	Yes, mono only
Laser Guaranteed	Yes, mono only
Permanence of Paper	Yes, meets ISO9706 requirements for Permanence of Paper

Environmental Information

Fibre Source	Virgin wood fibre from USA, Chile, Canada and Sweden
Bleaching	Pulp is bleached using an Elemental Chlorine Free (ECF) process
Disposal	This material can be disposed of by recycling, incineration for energy recovery, composting or is biodegradable
Accreditation	Produced at a mill that is certified with the ISO14001 environmental management standard PEFC Certified