

## REACTO CB COATED BACK

Carbonless paper, coated on the back.

### Technical Specifications

Property	Standard	Unit	Value						Tolerance
			56	60	70	80	90	95	
CB			56	60	70	80	90	95	
Grammage	ISO 536	g/m2 gsm	56	60	70	80	90	95	± 4 %
Calibre	ISO 534	µm	74	78	88	98	113	117	± 5
Smoothness Bekk (TS)	ISO 5627	s	35	35	35	35	35	35	± 20
Brightness R457	ISO 2470	%	98	103	103	103	103	103	± 3
Opacity	ISO 2471	%	81	81	83	86	88	88	± 3
Breaking Length MD	ISO 1924-1	m	6.500						± 1.500
Absolute Humidity		%	5,8						± 0,3

Subject to change without notice.