

REACTO CF COATED FRONT

Carbonless paper, coated on the front.

Technical Specifications

Property	Standard	Unit	Value					Tolerance
CB			57	80	90	130	173	
Grammage	ISO 536	g/m2 gsm	57	80	90	130	173	± 4 %
Calibre	ISO 534	µm	70	90	105	140	200	± 5
Smoothness Bekk (TS)	ISO 5627	s	50	40	40	40	40	± 20
Brightness R457	ISO 2470	%	98	103	103	103	103	± 3
Breaking Length MD	ISO 1924-1	m	6.500					± 1.500
Absolute Humidity		%	5,8					± 0,3

Subject to change without notice.