

REACTO CFB COATED FRONT AND BACK

Carbonless paper, coated on both sides.

Technical Specifications

Property	Standard	Unit	Value		Tolerance
CB			53	60	
Grammage	ISO 536	g/m2 gsm	53	60	± 4 %
Calibre	ISO 534	µm	70	80	± 5
Smoothness Bekk (TS)	ISO 5627	s	45	45	± 20
Brightness R457	ISO 2470	%	92	92	± 3
Breaking Length MD	ISO 1924-1	m	6.500		± 1.500
Absolute Humidity		%	5,8		± 0,3

Subject to change without notice.