

## HP EVERYDAY

Substance g/m <sup>2</sup>	75
Caliper $\mu\text{m}$ (approx)	100
Opacity (ISO) %	92
Brightness (ISO) D65	110
Whiteness CIE D65	161
Smoothness (Bendtsen) ml/min TS	200
Smoothness (Bendtsen) ml/min WS	200
Rigidity (Taber Stiffness Units) 15° MD	2.3
Rigidity (Taber Stiffness Units) 15° CD	0.85
Surface pH	>7

### Technical Capability

Copier Guaranteed	Yes
Laser Guaranteed	Yes, mono only
Inkjet Guaranteed	Yes, mono only
Plain Paper Fax	Yes
Permanence of Paper	Yes, meets ISO9706 requirements for Permanence of Paper

### Environmental Information

Fibre Source	Virgin wood fibre from Brazil
Bleaching	Pulp is bleached using an Elemental Chlorine Free (ECF) process
Disposal	This material can be disposed of by recycling, incineration for energy recovery, and composting
Accreditation	Produced at a mill that is certified with the ISO14001 environmental management standard PEFC Certified